# REPORT DOCUMENTATION PAGE

Form Approved OMB No. 0704-0188

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE	3. REPORT TYPE AND DATES COVERED		
	October, 1997	Final Report 6/30/94-9/29-97		
4. TITLE AND SUBTITLE		5. FUNDING NUMBERS		
Modification of High T	Superconductors by To	1		

Implantation

F49620-94-1-0373

6. AUTHOR(S)

T. H. Geballe

AFOSR-TR-97

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Board of Trustees of Leland Stanford Junior University 857 Serra Stanford, CA 94305-4125

()554

9. SPONSORING MONITORING AGENCY NAME(S) AND ADDRESS(ES)

AFOSR/NE 110 Duncan Avenue, Suite B115 Bolling AFB, DC 20332-0001 Dr. Harold Weinstock

10. SPONSORING / MONITORING AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

124. DISTRIBUTION . AVAILABILITY STATEMENT

12b. DISTRIBUTION CODE

Unlimited

#### 13. ABSTRACT (Maximum 200 words)

The transport properties of La-Ca manganites with the perovskite structure have been investigated over a wide range of temperatures above room temperature, and over the whole La-Ca concentration range. They can be understood in terms of a model proposed by Emin and Holstein in which the charge carriers are small polarons diffusing by adiabatic hops. For the first time it has been demonstrated that polaron hopping in the presence of strong on-site coulomb interaction results in Mott-Hubbard insulating behavior.

19971103 087

14. SUBJECT TERMS			15. NUMBER OF PAGES
polaron hopping, man concentration depend	ganate perovskite films ence		16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFICATION OF ABSTRACT unclassified	20. LIMITATION OF ABSTRACT unlimited

Standard Form 298 (Pev. 2-89)

### FINAL REPORT

to the

# AIR FORCE OFFICE OF SCIENTIFIC RESEARCH

for a program in

# MODIFICATION OF HIGH T $_{\rm c}$ SUPERCONDUCTORS BY ION IMPLANTATION

for the period 6/30/94-9/29/97

under

AASERT GRANT F49620-94-1-0373

Principal Investigator Professor T. H. Geballe

Edward L. Ginzton Laboratory Stanford University Stanford, CA 94305-4085

DITIC QUALITAY INSPLICITED 8

October 1997

### Final Report

# MODIFICATION OF HIGH T<sub>c</sub> SUPERCONDUCTORS BY ION IMPLANTATION

# AASERT GRANT F49620-94-1-0373 for the period 6/30/94-9/29/97

The reported ability to introduce large concentrations of cations with good control over space and site occupancy into the superconducting cuprate perovskite family by ion implantation without causing undue damage to the structure was the basis for our initial work. However, further developments <sup>1,2</sup> showed that the perovskite structures were severely damaged by the large doping and that the results were due to miscalculation of the range of implant. As a result, the investigation was shifted to studies of the manganate perovskites which undergo an insulator-metal transition and show colossal magneto resistance when properly doped. Like the high Tc cuprates, these compounds are highly correlated and show unusual magnetic and transport data. When properly doped they order magnetically at temperatures up to room temperature. Although they show no superconducting behavior under presently known conditions, they can be grown as epitaxial heterostructures with superconductors.

The transport properties of La<sub>0.67</sub>Ca<sub>0.33</sub>MnO<sub>3</sub> were studied over a wide range of temperatures above the Curie temperature of 262 K and fit to the Emin-Holstein model of adiabatic small polaron hopping using quite reasonable parameters.<sup>3</sup> In the final year the conductivity measurements from 300 K to 1200 K of La<sub>c</sub>Ca<sub>1-c</sub>MnO<sub>3</sub> thin films, with doping from c = 0 to c = 1, show that the entire doping range fits the adiabatic small polaron model  $\sigma = (A/T)\exp(-E_a/kT)$ . Furthermore the c dependence of c explicitly shows the effects of on-site coulomb repulsion, i.e. a polaron cannot hop into an occupied site. Instead of increasing monotonically as more carriers are introduced, c starts to decrease at c = 0.8 and is reduced to almost zero when the lattice is full.<sup>4</sup> The approach to zero of c as c approaches 1 shows that the strong on-site coulomb interaction results in Mott-Hubbard-like insulator behavior.

# References

1. Q.Y. Ma. P. Dosanij, J. Carolan, and W. Hardy, Extended Abstracts 4th Int. Superconductive Electronics Conf., ISEC 1993, Aug. 11-14, Boulder Co., and private communication.

- 2. Private Communication with Dr. L. King at Conductus.
- 3. D.C. Worledge, G. Jeffrey Snyder, M.R. Beasley, and T.H. Geballe, "Anneal-Tunable Curie Temperature and Transport of La<sub>0.67</sub>Ca<sub>0.33</sub>MnO<sub>3</sub>" J. Appl. Phys 80, 5158-5161 (November 1, 1996).
- 4. D.C. Worledge, L. Mieville, and T.H. Geballe, "On-site Coulomb Repulsion in the Small Polaron System La<sub>c</sub>Ca<sub>1-c</sub>MnO<sub>3</sub>," (in press) *Phys. Rev. Lett*.

### Personnel:

Faculty: Professor T. H. Geballe

Graduate Students: Daniel Worledge, Jeffrey Snyder

### Publications:

- 1. D.C. Worledge, G. Jeffrey Snyder, M.R. Beasley, and T.H. Geballe, "Anneal-Tunable Curie Temperature and Transport of La<sub>0.67</sub>Ca<sub>0.33</sub>MnO<sub>3</sub>" J. Appl. Phys 80, 5158-5161 (November 1, 1996).
- 2. D.C. Worledge, L. Mieville, and T.H. Geballe, "On-site Coulomb Repulsion in the Small Polaron System La<sub>c</sub>Ca<sub>1-c</sub>MnO<sub>3</sub>," (in press) *Phys. Rev. Lett*.

# Meetings:

Daniel Worledge presented a paper at American Physical Society March Meeting, Kansas City, MO., March 17-21, 1997.

### Transitions:

None currently

New discoveries, inventions, or patent disclosures:

None

## Honors/Awards:

D. Worledge, NSF Fellowship

Jeffrey Snyder graduated with a PhD in Applied Physics and is currently employed at the Jet Propulsion Laboratory, Pasadena, California (available at University Microfiche, Ann Arbor, MI).